



**PAG Flooring Systems GmbH**  
D-38176 Wendeburg  
Germany  
Info@pag-flooring.com  
www.pag-flooring.com

## **PAGsports Jogging Track – Jogg21**

**Total Thickness 18-20mm**



### **2-Layer Elastic Seamless Jogging Track Flooring of 20mm total thickness**

It consists of a shock-pad base-layer of 18mm of SBR Granules mixed with MDI PU Binder and a second layer of flexible PU pore-filler followed by UV resistant aliphatic top-coat.

#### **1.0 Build-Up**

**Subbase** of fully cured (at least 28 days) asphalt or concrete free of any dirt or spillage, that might prevent bonding of the rubber to the asphalt.

**PU Primer PP1000** applied by roller on top of the subbase.

**SBR layer** consisting of **SBR1030** (granules of 1mm – 3mm size) mixed with PU Binder **PB3300** installed by paving machine at 18mm thickness.

**Pore-Filler** layer, consisting of 3-component pore-filler **PV3555** (red colour) applied with metal trowel to create a non-porous layer of 1-2mm thickness.

**UV-Protection layer** consisting of UV stable aliphatic protective top-coating **PP7000** applied in 2 coats by airless spray or roller. Optionally, silica sand can be added to the first coating to avoid a slippery surface during wetness.