



PAG Flooring Systems GmbH
D-38176 Wendeburg
Germany
Info@pag-flooring.com
www.pag-flooring.com

PAGsports Jogging Track – Jogg21

Total Thickness 18-20mm



2-Layer Elastic Seamless Jogging Track Flooring of 25-30mm total thickness

It consists of a shock-pad base-layer of 18mm of SBR Granules mixed with MDI PU Binder and a second layer of flexible PU pore-filler followed by UV resistant aliphatic top-coat.

1.0 Build-Up

Subbase of fully cured (at least 28 days) asphalt or concrete free of any dirt or spillage, that might prevent bonding of the rubber to the asphalt.

PU Primer PP1000 applied by roller on top of the subbase.

SBR layer consisting of **SBR1030** (granules of 1mm – 3mm size) mixed with PU Binder **PB3300** installed by paving machine at 18mm thickness.

EPDM layer consisting of **EPDM0515** (granules of 0.5 – 1.5mm size) mixed with PU Binder **PB3300** (18% in weight) installed by paving machine at 3mm – 10mm thickness

Pore-Filler layer, consisting of 3-component pore-filler **PV3555** (red colour) applied with metal trowel to create a non-porous layer of 1-2mm thickness.

UV-Protection layer consisting of UV stable aliphatic protective top-coating **PP7000** applied in 2 coats by airless spray or roller. Optionally, silica sand can be added to the first coating to avoid a slippery surface during wetness.